

OUTDOOR FIBER CABLE OM2

109-132XX

Phone
+33 75 864 2169

Email
info@angnetworks.com

Log 202, 5rue Albert Thomas, 38100
Grenoble, France.



Overview

- Category: OM2
- Outdoor Fiber Optic Cable with Steel Wire Support, designed for high tensile strength and crush resistance, ideal for reliable data transmission in demanding environments

Industry Standard

- IEC60332-3C

Applications


- Inter-building connectivity
- Backbone premise pathways
- Drop ceiling installations
- Suitable for 10Gbps Ethernet, 550Mgh Broadband Video, SAN, data center, and indoor any-purpose cable distribution.

Ordering Information

Part Number	Description
109-13206	6C OUT-DOOR ARMOR FIBER CABLE UNITUBE WITH STEEL WIRE SUPPORT 50/125 OM2
109-13208	8C OUT-DOOR ARMOR FIBER CABLE UNITUBE WITH STEEL WIRE SUPPORT 50/125 OM2
109-13212	12C OUT-DOOR ARMOR FIBER CABLE UNITUBE WITH STEEL WIRE SUPPORT 50/125 OM2

General Information

- Fiber Count: 2 to 48
- Colored Coating Fiber Dimension: 250µm±15µm,
- Loose Tube Dimension: 2.0mm±0.05mm
- Loose Tube Material: PBT
- Loose Tube Color: Natural
- Colored Coating Fiber Color:
 1. Blue
 2. Orange
 3. Green
 4. Brown
 5. Grey
 6. Natural
 7. Red
 8. Black
 9. Yellow
 10. Purple
 11. Pink
 12. Aqua
- Strength Member Material: Steel
- Strength Member Diameter: 1.2mm
- Outer Jacket Dimension: 9.0mm±0.3mm,
- Outer Jacket Material: PE
- Outer Jacket Color: Black
- Jacket Properties: Anti-corrosion, Anti-water, Anti-ultraviolet Radiation, Flame retardant, Environmentally harmless, etc.



Geometric Parameters

- Core Diameter: 50.0±2.5µm
- Cladding Diameter: 124.8±1.0µm
- Cladding Non-Circularity: ≤1.0
- Core-Cladding Concentricity Error: ≤1.0
- Coating Diameter: 245±5µm
- Coating Non-Circularity: ≤6.0
- Cladding-Coating Concentricity Error: ≤12.0

Optical Performance Parameters

- Bandwidth (min) 850nm: 200 MHz
- Bandwidth (min) 1300nm: 500 MHz
- Attenuation (max.) 850nm: ≤3.0 dB/km
- Attenuation (max.) 1300nm: ≤1.0 dB/km

Mechanical and Environmental Characteristics

Items	Unite	Specification
Tension (Long Term)	N	800
Tension (Short Term)	N	1600
Crush (Long Term)	N/10cm	300
Crush (Short Term)	N/10cm	1000
Min. Bend Radius (Dynamic)	mm	20D
Min. Bend Radius (Static)	mm	10D
Installation Temperature	°C	-20~+60
Operating Temperature	°C	-40~+70
Storage Temperature	°C	-40~+70

HEADQUARTERS



A&G Technologies CO., Limited,
Log 202, 5rue Albert Thomas, 38100
Grenoble, France.

+33 75 864 2169

REGIONAL OFFICE



A&G Technologies (HK) CO., Limited,
Room 803, Chevalier House, 45-51 Chatham Road
South, Tsim Sha Tsui, Kowloon, Hong Kong.

+852 5420 8788

CONNECT THE FUTURE



info@angnetworks.com



www.angnetworks.com